

DIMENSIONS			
Thickness	5.00 mm · $t_{max} - t_{min} \leq 0.50$ mm		
Length	1219.2 mm · $l_{max} - l_{min} \leq 0.50$ mm		
Width	181.10 ± 0.10 mm · $w_{max} - w_{min} \leq 0.20$ mm		
TOLERANCE			
Squareness	EN 16511	≤ 0.20 mm	
Straightness	EN 16511	≤ 0.30 mm / m	
Flatness Crosswise	EN 16511	Concave: ≤ 0.15% · convex: ≤ 0.20%	
Flatness Lengthwise	EN 16511	Concave: ≤ 0.50% · convex: ≤ 1.00%	
Openings between Elements	EN 16511	Average: ≤ 0.15 mm · max: ≤ 0.20 mm	
Height Difference between Elements	EN 16511	Average: ≤ 0.10 mm · max: ≤ 0.15 mm	
TEST			
Abrasion Resistance Method B	EN 16511	≥ 3000 cycles	
Impact Resistance	EN 16511	≥ 1200 mm	
Micro Scratch Resistance	EN 16511	≤ MSR-A1	
Stain Resistance	Group 1 & 2	EN 16511	Grade 5
	Group 3	EN 16511	Grade 4
Castor Chair Test	ISO 4918	No change in appearance after 25,000 cycles	
Effect of Furniture Leg	EN 16511	No visible damage	
Thickness Swelling	EN 16511	No swelling	
Residual Indentation	EN 16511	≤ 0.20mm	
Locking Strength	EN 16511	$f_{l0,2} \geq 1$ kN/m (length); $f_{s0,2} \geq 1.5$ kN/m (width)	
Dimensional Stability	EN 16511	≤ 0.25 %	
ENVIRONMENT			
Emission of Formaldehyde	CDPH	PASS	
PHYSICAL BEHAVIOR			
Fire Behaviour	EN 13501-1	Bfl-s1	
Slide Resistance	EN 13893	DS	
Thermal Resistance	EN 12667	0.01 (m ² K)/W	
Electrostatic Behaviour	EN 1815	Antistatic Floor Covering	
SOUND ABSORPTION QUALITIES			
Calculated Impact Insulation Class	ASTM E492-09	IIC 62	
Calculated Sound Transmission Class	ASTM E90-09	STC 60	

The data sheet is updated regularly to meet new technological standards. This version replaces all previous versions as well as those which are undated.
 SPC RIGID CORE Flooring of floating installation, Level of use according to EN 16511: Class 32
 FOR FLOORING TO BE USED IN LIVING AREAS AND COMMERCIAL PREMISES

USA PRODUCTION: 434 Industrial Park Road, Cartersville GA 30121 USA
T: 1 470 490 9135 **E:** info@rokplank.net | orders@rokplank.net | sedat@rokplank.net

SHOWROOM & DISTRIBUTION: 6251 Hwy 7 Woodbridge ON L4H 0L1, Canada - **T:** 1 416 410 0411
DISTRIBUTION CENTER #2: 8 Tracey Blvd Brampton ON L6T 5R9, Canada - **T:** 1 416 410 7014
BURSA TURKEY PRODUCTION: Turanköy Mah. Bulut Sok. No:1/4, Kestel/BURSA, TURKEY 16450